

WOODSTEP® PLUS - 21095000

PRODUCT DESCRIPTION

Woodstep Plus roll-out foam-backed dance flooring is a slightly textured, heavy-duty surface. It is a multi-layer textured Marley dance floor that looks like Maple wood and installs like any other vinyl dance floor. Exceptionally realistic wood design combines form, function, and ease of installation. Resists wear and tear. **Woodstep Plus** can be installed directly on a concrete slab or other tile or wood surface. Recommended for ballet, jazz, modern dance and virtually all movement activities except tap or other percussive shoe-style dancing.

SIZE & PACKAGING

Width:	4.92 FT 4'11" (1.5 M)
Full Roll Length:	86.5 FT (26.4 M)
Thickness:	.24 IN (6.0 MM)
Wear Layer:	.06 IN (1.5 MM)
Weight:	6.84 LBS/SY (3.7 KG/SM)

INSTALLATION

Woodstep Plus is to be unrolled or unraveled so that the exterior surface (dance surfaces) faces up. Never attempt to flip the flooring over.

All vinyl flooring must be acclimated for a period of 24 hours at the temperature which will be maintained for the life of the flooring and lie flat prior to installation. Reliance of adhesion to flatten flooring is inadvisable.

Flooring may be loose laid with top tape on the seams and along the perimeter, semi-permanently installed with double-faced tape or **ReUseIt®** with optional top tape depending on the techniques employed, or permanently adhered with a full-spread glue. When using double-faced tape, different practices may apply. 4" double-faced tape can be used lengthwise: 1) 3 lengths, down the middle and along the perimeter on the left and right side; 2) 2 strips, along the perimeter on the left and right side, or 3) the left side or the right side, and panel sharing when abutting an adjacent roll. One or two strips of double-faced tape will also be taped spanning the width at the end of the length. When using glue, **Woodstep Plus** should be installed with a pressure-sensitive adhesive using a "semi-dry" application.

Seam welding is not recommended. All seam welding should be done only by a professional.

Always clean newly installed Marley or vinyl flooring. See weekly maintenance directions below.

CLEANING

Broom sweep or vacuum daily to remove coarse dirt, dust and debris.

Spot clean when necessary to remove scuffs or caustic spills or residue.

Stagestep, 4701 Bath St, Bldg 46B, Philadelphia, PA 19137



CLEANING (continued)

Mop clean weekly or as required with **ProClean®**, a neutral detergent-degreaser using the two-bucket method. One bucket is for the **ProClean** (2 oz **ProClean** to a gallon of water). The second bucket is for clear water to rinse the mop. Mop dry. Although **ProClean** is a non-rinse product, it is always preferable to rinse and remove excess moisture with a towel or clean dry mop.

Do not use alcohol, ammonia, acetone, bleach, cleansers, vinegar, or solvents to clean surface. Exposure to sunlight can cause reduced life expectancy due to UV radiation. Change in temperature and humidity can negatively affect installation and non-slip characteristics.

HANDLING & STORAGE

Handling: Normal safe handling practices must be applied.

Always use a suitable core tube which is no less than the full width of the rolls and has an interior diameter of 4 inches or greater.

It is recommended that rolls are stored in the vertical position and restrained in position using safety chains or straps. If the flooring is moved in a horizontal position, do not rest flat surfaces above, and return to vertical position immediately after transit. Prolonged horizontal positioning may result in roll-set whereby the rolled material takes on an oval shaped, causing stretch marks and irreversible damage.

PHYSICAL PROPERTIES/TESTING

PROPERTIES	STANDARD	RESULT
Thickness	ASTM F386	6.0 mm (.24 in)
Wear Layer	ASTM F410	1.5 mm (.06 in)
Roll Size		1.5 m x 26.4 m = 39.6 m2
Total Weight		3700g/m2 (6.84 lbs/sy)
Sport Properties	ASTM F2772	Class 2
Force Reduction	ASTM F2569	≥ 27% - ≤ 33%
Impact Sound Insulation	EN ISO 171-2	19 dB
Fire Rating	ASTM E648	Class 1
Naturally Bacteriostatic: Combats MRSA, E. coli and S. aureus*		OK
Allergen Free		OK
Indoor Air Quality /	EQc2	FloorScoreR Certified
Low Emitting Materials	LEED v4	
TVOC After 28 Days	ISO 16000-6	<100 µg/m3
Ease of Maintenance		No Wax, No Buff - for Life / PUR ProtectR
Restriction Use of	MRc4	Complies with REACH
Harmful Chemicals	LEED v4	

